

VERSTEE

== LEATHER ==

TECHNISCHE FICHE

| | |
|-------------|-------------------|
| ARTIKELNAAM | MARIS Outdoorstof |
| PRODUCTIE | ITALIE |
| ROLBREEDTE | 145 CM |
| ROLLENGTE | 40 M |

| TEST | TEST METHOD | RESULT |
|------------------------------------|-------------------------|------------------------------------|
| PHYSICAL | | |
| Weight | DIN 53352 | 365 gr/m ² |
| Composition | | 100% Solution dyed outdoor acrylic |
| STRENGTH | | |
| Tear strength | UNI EN ISO 13937-3 Warp | ≥ 246 N |
| | UNI EN ISO 13937-3 Weft | ≥ 273 N |
| Martindale | EN ISO 12947-2 | ≥ 13.000 cycles |
| Tensile strength | UNI EN ISO 13934-1 Warp | ≥ 1.900 N |
| | UNI EN ISO 13934-1 Weft | ≥ 1600 N |
| Color fastness to light | DIN 75202 | ≥ 8 (blue scale) |
| Adhesion | DIN EN ISO 2411 Warp | ≥ 20 N/5 cm |
| | DIN EN ISO 2411 Weft | ≥ 20 N/5 cm |
| Elongation | UNI EN ISO 13934-1 Warp | ≥ 30% |
| | UNI EN ISO 13934-1 Weft | ≥ 30% |
| Resistance to shrinking 30°C water | DIN EN ISO 105-E02 Warp | ≥ 1% |
| | DIN EN ISO 105-E02 Weft | ≥ 1% |
| SAFETY | | |
| Flame-retardant UK | BS 5852-1 | Passed |
| Resistance to oil and water | Teflon finish | Passed |