

# VERSTEE

== LEATHER ==

## TECHNICAL SPECIFICATION SHEET

ARTICLE NAME	CORTE
RAW MATERIAL	BOVINE HIDES
AVERAGE SIZE	14-16 sqft
THICKNESS	1,1-1,3 mm
TYPE OF GRAIN	SUEDE
TYPE OF TANNING	CHROME
ORIGIN	ITALY - EUROPE CEE

### Wij laten de kleuren fixeren

TEST	TEST METHOD	RESULT
Colour fastness to rubbing		
Nr. 50 dry rubs	IUF 450/UNI EN ISO 11640	≥ 3 grey scale
Nr. 20 wet rubs	IUF 450/UNI EN ISO 11640	≥ 2/3 grey scale
Flexing endurance		
	IUP 20/UNI EN ISO 5402	≥ 20000
Tear strength		
	IUP 40/UNI EN ISO 3377-1	≥ 60 N
Cigarette test (California)		
	IUP 40/UNI EN ISO 3377-1	Passed
Light resistance*		
	IUF 402/UNI EN ISO 105-B02	≥ 2/3

# VERSTEE

== LEATHER ==

Chromium VI		
	UNI EN ISO 17075-1:2017	None detected (detection limit: 3 mg/kg)
AZO dyestuffs - Arylamines		
	UNI EN ISO 17234-1:2015	None detected
	UNI EN ISO 17234-2:2011	detection limit: 30 mg/kg)
Formaldehyde		
	UNI EN ISO 17226-1:2008	< 20 mg/kg
Chlorinated phenols		
PCP TCP and TeCP	UNI EN ISO 17070:2015	None detected (detection limit: 1,0 mg/kg)

\* This parameter refers to an average value of the color tange